中国认可
检测
TESTING
CNAS L0748

230014349552

NO.1124010288

# 检 测 报 告

# Test Report

| | |
|---|---|
| 样品名称： | 锂离子聚合物电池 Li3949T44P8h906450-5A 3.85V 4870mAh/18.8Wh(RATED) 5000mAh/19.3Wh(TYPICAL) |
| Name of Sample: | RECHARGEABLE LI-ION POLYMER BATTERY Li3949T44P8h906450-5A 3.85V 4870mAh/18.8Wh(RATED) 5000mAh/19.3Wh(TYPICAL) |
| 委托单位: | 中山天贸电池有限公司 |
| Consignor: | Zhongshan Tianmao Battery Co., LTD. |

上海化工院检测有限公司

Shanghai Institute of Chemical Industry Testing Co., Ltd.

# 上海化工院检测有限公司
# 检 测 报 告

Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report

NO. 1124010288



| | | | | |
|---|---|---|---|---|
| 样品名称 Name of Sample | 中文 Chinese | 锂离子聚合物电池 Li3949T44P8h906450-5A 3.85V 4870mAh/18.8Wh(RATED) 5000mAh/19.3Wh(TYPICAL) | | |
| | 英文 English | RECHARGEABLE LI-ION POLYMER BATTERY Li3949T44P8h906450-5A 3.85V 4870mAh/18.8Wh(RATED) 5000mAh/19.3Wh(TYPICAL) | | |
| 样品编号 Sample No. | 1124010288 | | | |
| 委托单位 Consignor | 中山天贸电池有限公司 Zhongshan Tianmao Battery Co., LTD. | | | |
| 生产单位 Manufacturer | 中山天贸电池有限公司 Zhongshan Tianmao Battery Co., LTD. | | | |
| 检测方法 Test method | 联合国《试验和标准手册》 ST/SG/AC.10/11/Rev.7&Amend.1 38.3 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 | | | |
| 判定标准 Criterion | 联合国《试验和标准手册》 ST/SG/AC.10/11/Rev.7&Amend.1 38.3 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 | | | |
| 样品外观 Appearance | 黑色 塑料薄膜外壳 Black Plastic film shell | | | |
| 样品接受日期 Accepted Date | 2024-01-09 | 检测起迄日期 Test Date | 2024-01-11 ～ 2024-02-21 | |
| 检测项目 Test Items | 高度模拟;热测试;振动;冲击;外短路;挤压;过充电;强制放电 Altitude simulation, Thermal test, Vibration, Shock, External short circuit, Crush, Overcharge, Forced discharge | | | |
| 检测结论 Conclusion | 经检测，该样品符合联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3标准要求。 The sample has passed the test items of UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 生效日期(Date)： 2024-02-21 | | | |
| 备注 Comment | 可充电单电芯电池Rechargeable Single Cell Battery./ | | | |
| 委托单位地址 Consignor Address | / | | 邮政编码 Post Code | / |

批准 Approver: 许鑫　审核 Checker: 陆建峰　编制 Compiler: 傅俊

职务 Title: 电化学测试部部长(Head of Electrochemical Testing Department)

| 序号 No. | 检测项目名称 Name of Test Items | 标准要求或标准条款号 Standard requirement or The Clause Number of Standard | 检测结果 Test Result | 本项结论 Conclusion | 备注 Remark |
|---|---|---|---|---|---|
| 1 | 高度模拟 Altitude simulation | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.1 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.1 | 见附表 1 See Appendix 1 | 合格 Passed | / |
| 2 | 热测试 Thermal test | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.2 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.2 | 见附表 2 See Appendix 2 | 合格 Passed | / |
| 3 | 振动 Vibration | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.3 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.3 | 见附表 3 See Appendix 3 | 合格 Passed | / |
| 4 | 冲击 Shock | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.4 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.4 | 见附表 4 See Appendix 4 | 合格 Passed | / |
| 5 | 外短路 External short circuit | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.5 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.5 | 见附表 5 See Appendix 5 | 合格 Passed | / |
| 6 | 挤压 Crush | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.6 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.6 | 见附表 6 See Appendix 6 | 合格 Passed | / |
| 7 | 过充电 Overcharge | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.7 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.7 | 见附表 7 See Appendix 7 | 合格 Passed | / |
| 8 | 强制放电 Forced discharge | 联合国《试验和标准手册》ST/SG/AC.10/11/Rev.7&Amend.1 38.3 试验T.8 UN Manual of Tests and Criteria ST/SG/AC.10/11/Rev.7&Amend.1 Section 38.3 Test T.8 | 见附表 8 See Appendix 8 | 合格 Passed | / |

| | | | | | |
|---|---|---|---|---|---|
| 检测环境条件 Test Environment Condition | 环境温度:20℃-21℃;环境湿度:/% Ambient temperature:20℃-21℃;Ambient humidity:/% | | | | |
| 分包检验情况 Subcontracted Test Condition | 检测项目 Test Item | / | | | |
| | 分包实验室 Subcontracted Laboratory | 名称 Name | / | 邮编 Post Code | / |
| | | 地址 Address | / | 电话 Tel | / |

# 上海化工院检测有限公司
# 检 测 报 告－附表1

Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report—Appendix 1

NO. 1124010288



| 序号 No. | 1 | 检测项目名称 Name of Test Items | | 高度模拟 Altitude simulation | | | | |
|---|---|---|---|---|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 试验前 Before | | 试验后 After | | 质量损失 Mass Loss /% | 剩余电压 Residual OCV /% | 其他现象 Other Event |
| | | 质量 Mass /g | 开路电压 OCV /V | 质量 Mass /g | 开路电压 OCV /V | | | |
| 001 | 1CYC完全充电 1CYC Fully charged | 65.9897 | 4.36 | 65.9864 | 4.36 | 0.01 | 100.00 | O |
| 002 | 1CYC完全充电 1CYC Fully charged | 66.1187 | 4.36 | 66.1178 | 4.36 | 0.00 | 100.00 | O |
| 003 | 1CYC完全充电 1CYC Fully charged | 65.9771 | 4.36 | 65.9676 | 4.36 | 0.01 | 100.00 | O |
| 004 | 1CYC完全充电 1CYC Fully charged | 65.8234 | 4.36 | 65.8124 | 4.36 | 0.02 | 100.00 | O |
| 005 | 1CYC完全充电 1CYC Fully charged | 64.9922 | 4.36 | 64.9823 | 4.35 | 0.02 | 99.77 | O |
| 006 | 25CYC完全充电 25CYC Fully charged | 65.8041 | 4.36 | 65.7988 | 4.36 | 0.01 | 100.00 | O |
| 007 | 25CYC完全充电 25CYC Fully charged | 65.6405 | 4.36 | 65.6342 | 4.36 | 0.01 | 100.00 | O |
| 008 | 25CYC完全充电 25CYC Fully charged | 66.0013 | 4.36 | 65.9944 | 4.36 | 0.01 | 100.00 | O |
| 009 | 25CYC完全充电 25CYC Fully charged | 66.0489 | 4.35 | 66.0436 | 4.35 | 0.01 | 100.00 | O |
| 010 | 25CYC完全充电 25CYC Fully charged | 65.6908 | 4.36 | 65.6779 | 4.35 | 0.02 | 99.77 | O |
| 以下空白 | This space intentionally left blank | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |

备注：L-泄漏 V-漏气 D-解体 R-破裂 F-起火 O-无泄漏、无漏气、无解体、无破裂、无起火。
Note: L-Leakage V-Venting D-Disassembly R-Rupture F-Fire O-No Leakage,No Venting, No Disassembly,No Rupture & No Fire.

# 上海化工院检测有限公司
# 检 测 报 告 - 附表2

Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report — Appendix 2



| 序号 No. | 2 | 检测项目名称 Name of Test Items | | 热测试 Thermal test | | | | |
|---|---|---|---|---|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 试验前 Before | | 试验后 After | | 质量损失 Mass Loss /% | 剩余电压 Residual OCV /% | 其他现象 Other Event |
| | | 质量 Mass /g | 开路电压 OCV /V | 质量 Mass /g | 开路电压 OCV /V | | | |
| 001 | 1CYC完全充电 1CYC Fully charged | 65.9864 | 4.36 | 65.9785 | 4.28 | 0.01 | 98.17 | O |
| 002 | 1CYC完全充电 1CYC Fully charged | 66.1178 | 4.36 | 66.1066 | 4.28 | 0.02 | 98.17 | O |
| 003 | 1CYC完全充电 1CYC Fully charged | 65.9676 | 4.36 | 65.9641 | 4.28 | 0.01 | 98.17 | O |
| 004 | 1CYC完全充电 1CYC Fully charged | 65.8124 | 4.36 | 65.8121 | 4.28 | 0.00 | 98.17 | O |
| 005 | 1CYC完全充电 1CYC Fully charged | 64.9823 | 4.35 | 64.9802 | 4.28 | 0.00 | 98.39 | O |
| 006 | 25CYC完全充电 25CYC Fully charged | 65.7988 | 4.36 | 65.7932 | 4.28 | 0.01 | 98.17 | O |
| 007 | 25CYC完全充电 25CYC Fully charged | 65.6342 | 4.36 | 65.6304 | 4.28 | 0.01 | 98.17 | O |
| 008 | 25CYC完全充电 25CYC Fully charged | 65.9944 | 4.36 | 65.9907 | 4.28 | 0.01 | 98.17 | O |
| 009 | 25CYC完全充电 25CYC Fully charged | 66.0436 | 4.35 | 66.0377 | 4.28 | 0.01 | 98.39 | O |
| 010 | 25CYC完全充电 25CYC Fully charged | 65.6779 | 4.35 | 65.6794 | 4.28 | 0.00 | 98.39 | O |
| 以下空白 | This space intentionally left blank | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |

备注：L-泄漏 V-漏气 D-解体 R-破裂 F-起火 O-无泄漏、无漏气、无解体、无破裂、无起火。
Note: L-Leakage V-Venting D-Disassembly R-Rupture F-Fire O-No Leakage,No Venting, No Disassembly,No Rupture & No Fire.

# 上海化工院检测有限公司
# 检 测 报 告－附表3

Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report—Appendix 3

NO. 1124010288



| 序号 No. | 3 | 检测项目名称 Name of Test Items | | 振动 Vibration | | | | |
|---|---|---|---|---|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 试验前 Before | | 试验后 After | | 质量损失 Mass Loss /% | 剩余电压 Residual OCV /% | 其他现象 Other Event |
| | | 质量 Mass /g | 开路电压 OCV /V | 质量 Mass /g | 开路电压 OCV /V | | | |
| 001 | 1CYC完全充电 1CYC Fully charged | 65.9785 | 4.28 | 65.9768 | 4.20 | 0.00 | 98.13 | O |
| 002 | 1CYC完全充电 1CYC Fully charged | 66.1066 | 4.28 | 66.1049 | 4.28 | 0.00 | 100.00 | O |
| 003 | 1CYC完全充电 1CYC Fully charged | 65.9641 | 4.28 | 65.9636 | 4.28 | 0.00 | 100.00 | O |
| 004 | 1CYC完全充电 1CYC Fully charged | 65.8121 | 4.28 | 65.8120 | 4.28 | 0.00 | 100.00 | O |
| 005 | 1CYC完全充电 1CYC Fully charged | 64.9802 | 4.28 | 64.9795 | 4.28 | 0.00 | 100.00 | O |
| 006 | 25CYC完全充电 25CYC Fully charged | 65.7932 | 4.28 | 65.7923 | 4.28 | 0.00 | 100.00 | O |
| 007 | 25CYC完全充电 25CYC Fully charged | 65.6304 | 4.28 | 65.6278 | 4.27 | 0.00 | 99.77 | O |
| 008 | 25CYC完全充电 25CYC Fully charged | 65.9907 | 4.28 | 65.9892 | 4.28 | 0.00 | 100.00 | O |
| 009 | 25CYC完全充电 25CYC Fully charged | 66.0377 | 4.28 | 66.0365 | 4.26 | 0.00 | 99.53 | O |
| 010 | 25CYC完全充电 25CYC Fully charged | 65.6794 | 4.28 | 65.6783 | 4.28 | 0.00 | 100.00 | O |
| 以下空白 | This space intentionally left blank | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |

备注：L-泄漏 V-漏气 D-解体 R-破裂 F-起火 O-无泄漏、无漏气、无解体、无破裂、无起火。
Note: L-Leakage V-Venting D-Disassembly R-Rupture F-Fire O-No Leakage,No Venting, No Disassembly,No Rupture & No Fire.

# 上海化工院检测有限公司
## 检 测 报 告－附表4
Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report—Appendix 4



| 序号 No. | 4 | 检测项目名称 Name of Test Items | | 冲击 Shock | | | | |
|---|---|---|---|---|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 试验前 Before | | 试验后 After | | 质量损失 Mass Loss /% | 剩余电压 Residual OCV /% | 其他现象 Other Event |
| | | 质量 Mass /g | 开路电压 OCV /V | 质量 Mass /g | 开路电压 OCV /V | | | |
| 001 | 1CYC完全充电 1CYC Fully charged | 65.9768 | 4.20 | 65.9736 | 4.20 | 0.00 | 100.00 | O |
| 002 | 1CYC完全充电 1CYC Fully charged | 66.1049 | 4.28 | 66.0976 | 4.28 | 0.01 | 100.00 | O |
| 003 | 1CYC完全充电 1CYC Fully charged | 65.9636 | 4.28 | 65.9612 | 4.28 | 0.00 | 100.00 | O |
| 004 | 1CYC完全充电 1CYC Fully charged | 65.8120 | 4.28 | 65.8012 | 4.28 | 0.02 | 100.00 | O |
| 005 | 1CYC完全充电 1CYC Fully charged | 64.9795 | 4.28 | 64.9782 | 4.28 | 0.00 | 100.00 | O |
| 006 | 25CYC完全充电 25CYC Fully charged | 65.7923 | 4.28 | 65.7917 | 4.28 | 0.00 | 100.00 | O |
| 007 | 25CYC完全充电 25CYC Fully charged | 65.6278 | 4.27 | 65.6269 | 4.27 | 0.00 | 100.00 | O |
| 008 | 25CYC完全充电 25CYC Fully charged | 65.9892 | 4.28 | 65.9799 | 4.28 | 0.01 | 100.00 | O |
| 009 | 25CYC完全充电 25CYC Fully charged | 66.0365 | 4.26 | 66.0314 | 4.26 | 0.01 | 100.00 | O |
| 010 | 25CYC完全充电 25CYC Fully charged | 65.6783 | 4.28 | 65.6758 | 4.28 | 0.00 | 100.00 | O |
| 以下空白 | This space intentionally left blank | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |
| | | | | | | | | |

备注：L-泄漏 V-漏气 D-解体 R-破裂 F-起火 O-无泄漏、无漏气、无解体、无破裂、无起火。
Note: L-Leakage V-Venting D-Disassembly R-Rupture F-Fire O-No Leakage,No Venting, No Disassembly,No Rupture & No Fire.

# 上海化工院检测有限公司
# 检 测 报 告－附表5
Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report—Appendix 5



| 序号 No. | 5 | 检测项目名称 Name of Test Items | 外短路 External short circuit |
|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 样品表面最高温度 Max. External Temperature /℃ | 其他现象 Other Event |
| 001 | 1CYC完全充电 1CYC Fully charged | 57.4 | O |
| 002 | 1CYC完全充电 1CYC Fully charged | 57.4 | O |
| 003 | 1CYC完全充电 1CYC Fully charged | 57.0 | O |
| 004 | 1CYC完全充电 1CYC Fully charged | 56.0 | O |
| 005 | 1CYC完全充电 1CYC Fully charged | 56.9 | O |
| 006 | 25CYC完全充电 25CYC Fully charged | 57.7 | O |
| 007 | 25CYC完全充电 25CYC Fully charged | 56.9 | O |
| 008 | 25CYC完全充电 25CYC Fully charged | 57.2 | O |
| 009 | 25CYC完全充电 25CYC Fully charged | 57.7 | O |
| 010 | 25CYC完全充电 25CYC Fully charged | 57.9 | O |
| 以下空白 | This space intentionally left blank | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

备注：D-解体 R-破裂 F-起火 O-无解体、无起火、无破裂。
Note: D-Disassembly R-Ruptur F-Fire O-No Disassembly,No Fire & No Rupture.

# 上海化工院检测有限公司
# 检 测 报 告－附表6
Shanghai Institute of Chemical Industry
Testing Co., Ltd. Test Report—Appendix 6



| 序号 No. | 6 | 检测项目名称 Name of Test Items | 挤压 Crush |
|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 样品表面最高温度 Max. External Temperature /℃ | 其他现象 Other Event |
| 011 | 1CYC 50%容量 1CYC 50% Capacity | 21.4 | O |
| 012 | 1CYC 50%容量 1CYC 50% Capacity | 21.5 | O |
| 013 | 1CYC 50%容量 1CYC 50% Capacity | 21.9 | O |
| 014 | 1CYC 50%容量 1CYC 50% Capacity | 21.7 | O |
| 015 | 1CYC 50%容量 1CYC 50% Capacity | 21.5 | O |
| 016 | 25CYC 50%容量 25CYC 50% Capacity | 21.3 | O |
| 017 | 25CYC 50%容量 25CYC 50% Capacity | 21.4 | O |
| 018 | 25CYC 50%容量 25CYC 50% Capacity | 21.7 | O |
| 019 | 25CYC 50%容量 25CYC 50% Capacity | 21.1 | O |
| 020 | 25CYC 50%容量 25CYC 50% Capacity | 21.5 | O |
| 以下空白 | This space intentionally left blank | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

备注：D-解体 F-起火 O-无解体、无起火。
Note: D-Disassembly F-Fire O-No Disassembly & No Fire.

| 序号 No. | 7 | 检测项目名称 Name of Test Items | 过充电 Overcharge |
|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 其他现象 Other Event | |
| 021 | 1CYC完全充电 1CYC Fully charged | O | |
| 022 | 1CYC完全充电 1CYC Fully charged | O | |
| 023 | 1CYC完全充电 1CYC Fully charged | O | |
| 024 | 1CYC完全充电 1CYC Fully charged | O | |
| 025 | 25CYC完全充电 25CYC Fully charged | O | |
| 026 | 25CYC完全充电 25CYC Fully charged | O | |
| 027 | 25CYC完全充电 25CYC Fully charged | O | |
| 028 | 25CYC完全充电 25CYC Fully charged | O | |
| 以下空白 | This space intentionally left blank | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |
| | | | |

备注：D-解体 F-起火 O-无解体、无起火。
Note: D-Disassembly F-Fire O-No Disassembly & No Fire.

| 序号 No. | 8 | 检测项目名称 Name of Test Items | 强制放电 Forced discharge |
|---|---|---|---|
| 样品编号 Sample No. | 样品状态 Sample Status | 其他现象 Other Event | |
| 029 | 1CYC完全放电 1CYC Fully discharged | O | |
| 030 | 1CYC完全放电 1CYC Fully discharged | O | |
| 031 | 1CYC完全放电 1CYC Fully discharged | O | |
| 032 | 1CYC完全放电 1CYC Fully discharged | O | |
| 033 | 1CYC完全放电 1CYC Fully discharged | O | |
| 034 | 1CYC完全放电 1CYC Fully discharged | O | |
| 035 | 1CYC完全放电 1CYC Fully discharged | O | |
| 036 | 1CYC完全放电 1CYC Fully discharged | O | |
| 037 | 1CYC完全放电 1CYC Fully discharged | O | |
| 038 | 1CYC完全放电 1CYC Fully discharged | O | |
| 039 | 25CYC完全放电 25CYC Fully discharged | O | |
| 040 | 25CYC完全放电 25CYC Fully discharged | O | |
| 041 | 25CYC完全放电 25CYC Fully discharged | O | |
| 042 | 25CYC完全放电 25CYC Fully discharged | O | |
| 043 | 25CYC完全放电 25CYC Fully discharged | O | |
| 044 | 25CYC完全放电 25CYC Fully discharged | O | |
| 045 | 25CYC完全放电 25CYC Fully discharged | O | |
| 046 | 25CYC完全放电 25CYC Fully discharged | O | |
| 047 | 25CYC完全放电 25CYC Fully discharged | O | |
| 048 | 25CYC完全放电 25CYC Fully discharged | O | |

备注：D-解体 F-起火 O-无解体、无起火。
Note: D-Disassembly F-Fire O-No Disassembly & No Fire.


ZTE
Li-ion 00
生产厂:中山天贸电池有限公司
额定容量/RATED CAPACITY:4870mAh
额定能量/RATED WATT HOUR:18.8Wh
典型容量/TYPICAL CAPACITY:5000mAh
典型能量/TYPICAL WATT HOUR:19.3Wh
标称电压/NOMINAL VOLTAGE:3.85V
充电限制电压/LIMITED CHARGE VOLTAGE:4.4V
型号/MODEL:Li3949T44P8h906450-5A

***报告结束***